

	Type	Hits	Search Text	DBs
1	BRS	4	"6814914"	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT
2	BRS	6	"5793020"	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT
3	BRS	19	"5193020"	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT
4	BRS	25	"5518783"	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT
5	BRS	17	"644439"	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT
6	BRS	2	"9418583"	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT
7	BRS	468	positive near birefringence	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT
8	BRS	381	349/118	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT

	Type	Hits	Search Text	DBs
9	BRS	994	349/122	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT
10	BRS	27	S9 and S10	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT
11	BRS	1	10/502296	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT
12	BRS	94	428/1.5	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT
13	BRS	9	S13 and S10	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT
14	BRS	20157	anti-cracking or anticracking or antistress or anti-stress or (stress near (prevent\$4 or eliminat\$4))	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT
15	BRS	117263 0	adhesive or (bonding near agent)	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT
16	BRS	648	S15 same S16	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT

	Type	Hits	Search Text	DBs
17	BRS	1314864	compensat\$6 or retard\$6	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT
18	BRS	105	S17 and S18	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT
19	BRS	543	S17 not S19	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT
20	BRS	2	"6900937"	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT
21	BRS	3	"6590625"	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT
22	BRS	2	"6621635"	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT
23	BRS	2	"6560022"	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT
24	BRS	26	"2692035"	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT

	Type	Hits	Search Text	DBs
25	BRS	17	"5635105"	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT
26	BRS	2	"2001350021"	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT
27	BRS	2	"2001305345"	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT
28	BRS	40	"120620"	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT
29	BRS	131981 1	compensat\$6 or retard\$6	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT
30	BRS	176536 6	protecti\$5	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT
31	BRS	36673	S30 same S31	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT
32	BRS	206983	\$5isocyanate or polyisocyanate	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT

	Type	Hits	Search Text	DBs
33	BRS	7389	S33 same S31	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT
34	BRS	204	S32 same S34	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT
35	BRS	344	S32 and S34	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT
36	BRS	140	S36 not S35	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT
37	BRS	6500	S30 same S33	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT
38	BRS	7141	S33 same (hardness or microhardness)	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT
39	BRS	1123	S39 same layer	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT
40	BRS	143	S30 and S40	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT

	Type	Hits	Search Text	DBs
41	BRS	88	S40 same flexible	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT
42	BRS	0	S40 same gpascal	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT
43	BRS	1	S40 same gigapascal	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT
44	BRS	4	S40 same gpa	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT
45	BRS	6	S39 same gpa	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT
46	BRS	1	S40 same pascal	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT
47	BRS	19	S40 same pa	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT
48	BRS	3	S39 same pascal	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT

	Type	Hits	Search Text	DBs
49	BRS	298	(hardness or microhardness) near gpa	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT
50	BRS	24261	S31 same (urethane or polyurethane)	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT
51	BRS	1422	S51 and S30 and S33	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT
52	BRS	412	S52 and optical	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT
53	BRS	1	10/502296	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT
54	BRS	53	hardcoat same S33	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT
55	BRS	176536 6	protecti\$5	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT
56	BRS	206983	\$5isocyanate or polyisocyanate	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT

	Type	Hits	Search Text	DBs
57	BRS	7389	S57 same S56	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT
58	BRS	1419	S58 same (glue or adhesive or binder)	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT
59	BRS	680	S59 same layer	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT
60	BRS	38	S59 same optical	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT
61	BRS	257	S59 and optical	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT
62	BRS	219	S62 not S61	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT
63	BRS	19	"5193020"	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT
64	BRS	4	"5730899"	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT

	Type	Hits	Search Text	DBs
65	BRS	119	"5506704"	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT
66	BRS	131981 1	compensat\$6 or retard\$6	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT
67	BRS	2091	(lcd or (liquid near crystal near display)) same (el or electrolumin\$8) same (pd or plasma) same (fed or (field near emission))	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT
68	BRS	360	S67 and S68	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT
69	BRS	44	S67 same S68	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT
70	BRS	316	S69 not S70	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT
71	BRS	10	"5976297"	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT